



This MotoCAP safety rating applies to:

Brand: RST

Model: Ventilator V CE

Type: Jacket - Textile

Date purchased: 11 February 2019

Sizes tested: 52 and 54

Gender: M

Style: All Purpose Test code: J19T06


Test Results Summary:

	Rating	Score
MotoCAP Protection Rating	**	39.4
Abrasion	2/10	1.37
Burst	10/10	1554
Impact	8/10	56.8
MotoCAP Comfort Rating	****	0.990
Moisture Vapour Resistance		12.0
Thermal Resistance		0.198
Water resistance	1/10	87

This garment is fitted with impact protectors for the elbows and shoulders. Pockets are provided at the back for aftermarket impact protectors. Mesh panels are located in the arms, chest and sides of the back to allow airflow cooling in hot weather. This garment was also tested with the water-resistant liner installed, which reduced the comfort rating to 4 stars

Jacket and Pants - Crash Impact Risk Zones

This diagram is a pictorial representation of the crash impact risk Zones.





Abrasion Resistance

The garment was tested for abrasion resistance in accordance with MotoCAP test protocols. The table below shows the test results for time to abrade through all layers of the materials. Calculated for each sample by Zone, type and area coverage of each material as a proportion of that Zone.

Details of materials used in garment:

Material A: High density fabric shell, laminated fabric layer and mesh inner liner

Material B: Mesh shell and mesh inner liner
Material C: Fabric shell and mesh inner liner

Zone	Coverage	Abrasion t	time for eac	ch test (sec	onds)			Average
	(%)	1	2	3	4	5	6	(seconds)
Zone 1 and 2	areas (High abra	asion risk)						
Material A	100%	2.48	1.21	1.73	3.29	1.21	1.71	1.94 M
	Medium abrasio			0.45				
Material B	35%	0.90	0.70	0.47	0.77	0.49	0.39	0.62 P
Material C	65%	0.54	0.66	0.33	0.31	0.34	0.34	0.42 P
Zone 4 area (Low abrasion ris	sk)						
Material B	25%	0.54	0.66	0.33	0.31	0.34	0.34	0.42 M
Material C	75%	0.90	0.70	0.47	0.77	0.49	0.39	0.62 M

Abrasion times are capped at a maximum of 10.00s.

The diagram below is a visual indication of the likely abrasion performance of the materials in each zone calculated from the data in the table above. The colour coding is based on the worst performing material in each zone.



		Good	Acceptable	Marginal	Poor
Determining Criteria					
High abrasion risk	Zone 1/2:	> 5.6	3.0 - 5.6	1.3 - 2.9	< 1.3
Medium abrasion risk	Zone 3:	> 2.5	1.8 - 2.5	0.8 - 1.7	< 0.8
Low abrasion risk	Zone 4:	>1.5	1.0 - 1.5	0.4 - 0.9	< 0.4




Burst Strength

The garment's burst strength was tested in accordance with MotoCAP test protocols. The table below shows the burst pressure in kilopascals (kPA) for each sample tested by Zone and the average result for each zone.

Burst pressure (kPA)

Area	1	2	3	4	5	Average
Zones 1 & 2	1946	1952	1673	1718	1946	1847 G
Zone EZ	1944	1480	1272	1506	1386	1517 G
Zones 3 & 4	551	1064	952	1123	1504	1039 G

The diagram below illustrates the burst strength results in terms of the likely performance of the garment in an impact and is a pictorial representation of the data from the table above.





Impact Protection


The garment was tested for impact protection and coverage in accordance with MotoCAP test protocols. The table below shows the test results for each strike on each impact protector in kilonewtons (kN) and their area of coverage as a proportion (%) of the Zone.

Impact protector type	Elbow		Shoulder
Average force (kN)	16.7	A	17.9 A
Maximum force (kN)	20.4	A	20.0 A
Coverage of zone 1 area	120%		120%
Coverage of zone after displacement	100%		100%

Individual test results

Impact force (kN)	Elbow			Shoulder		
Strike location	Α	В	С	A	В	С
Impact Protector 1	17.8	14.8	18.8	13.6	17.4	20.0
Impact Protector 2	11.7	16.1	19.8	15.6	17.6	19.5
Impact Protector 3	11.8	19.1	20.4	18.2	19.0	20.0

The diagram below is a visual indication of the likely performance of each impact protector calculated from the data in the table above. The colour coding is based on the worst performing score for average or maximium force for each impact zone.



^{*} Poor may also indicate that no impact protector, or impact protector pocket is present in the garment Areas shaded black are not considered in the impact protection ratings.



Thermal comfort

The garment was tested for thermal comfort following the MotoCAP test protocols. The table below shows the moisture vapour resistance and the thermal resistance values obtained.

	1	2	Average
Moisture Vapour Resistance - Ret	12.9	11.1	12.0
(kPam²/W)			
	1	2	Average
Thermal Resistance - R _{ct}	0.199	0.196	0.198
(Km²/W)			

Water spray and rain resistance

This garment is advertised as water-resistant, and so has been tested for water spray and rain resistance according to the MotoCAP test protocols. The table below shows the water absorbed (ml) and the wetting proportion (%) of the garment and undergarments due to water absorption.

	Water absorbe	ed by garment	Water absorbe	ed by underwear
	Volume (ml)	Percentage (%)	Volume (ml)	Percentage (%)
Garment 1	870	47%	162	58%
Garment 2	702	38%	320	115%
Average	524	43%	241	87%

Location of wetting:

Visible wetting to the cotton underwear worn under the motorcycle water resistant garment was present at the cuffs of the sleeves, the upper arms, the chest and back.