



This MotoCAP safety rating applies to:

Brand: Rjays

Model: Lemans III Ladies

Type: Jacket - Textile

Date purchased: 13 May 2019

Sizes tested: XL and 2XL

Gender: F

Style: Sports Test code: J19T17


Test Results Summary:

	Rating	Score
MotoCAP Protection Rating	*	19.0
Abrasion	1/10	0.32
Burst	9/10	990
Impact	4/10	25.1
MotoCAP Comfort Rating	1	0.088
Moisture Vapour Resistance		223.2
Thermal Resistance		0.329
Water resistance	3/10	19.7

This garment is fitted with impact protectors for the elbows, shoulders and back. Vents are located in the front of the shoulders to allow airflow cooling in hot weather. The thermal comfort rating is based on tests of the breathability of the garment when all vents are closed. The thermal comfort of this product may be better when the vents can be opened.

Jacket and Pants - Crash Impact Risk Zones

This diagram is a pictorial representation of the crash impact risk Zones.





Abrasion Resistance

The garment was tested for abrasion resistance in accordance with MotoCAP test protocols. The table below shows the test results for time to abrade through all layers of the materials. Calculated for each sample by Zone, type and area coverage of each material as a proportion of that Zone.

Details of materials used in garment:

Material A: Qulited fabric shell, water resistant layer and mesh inner liner Material B: Woven fabric shell, water resistant layer and mesh inner liner

Zone	Coverage	Abrasion t	time for eac	ch test (sec	onds)			Average
	(%)	1	2	3	4	5	6	(seconds)
Zone 1 and 2	areas (High abra	asion risk)						
Material A	65%	0.90	0.59	2.11	1.20		2.72	1.50 M
Material B	35%	0.30	0.23	0.21	0.43	0.48	0.26	0.32 P
Zone 3 area (Medium abrasio	n risk)						
Material B	100%	0.30	0.23	0.21	0.43	0.48	0.26	0.32 P
Zone 4 area (Low abrasion ris	sk)						
Material B	100%	0.30	0.23	0.21	0.43	0.48	0.26	0.32 P

Abrasion times are capped at a maximum of 10.00s.

Page 2 of 5

The diagram below is a visual indication of the likely abrasion performance of the materials in each zone calculated from the data in the table above. The colour coding is based on the worst performing material in each zone.



		Good	Acceptable	Marginal	Poor
Determining Criteria					
High abrasion risk	Zone 1/2:	> 5.6	3.0 - 5.6	1.3 - 2.9	< 1.3
Medium abrasion risk	Zone 3:	> 2.5	1.8 - 2.5	0.8 - 1.7	< 0.8
Low abrasion risk	Zone 4:	>1.5	1.0 - 1.5	0.4 - 0.9	< 0.4




Burst Strength

The garment's burst strength was tested in accordance with MotoCAP test protocols. The table below shows the burst pressure in kilopascals (kPA) for each sample tested by Zone and the average result for each zone.

Burst pressure (kPA)

Area	1	2	3	4	5	Average	
Zones 1 & 2	1453	1344	1150	1244	1350	1308	G
Zone EZ	880	1011	662	585	907	809	A
Zones 3 & 4	302	343	675	1074	1171	713	M

The diagram below illustrates the burst strength results in terms of the likely performance of the garment in an impact and is a pictorial representation of the data from the table above.





Impact Protection


The garment was tested for impact protection and coverage in accordance with MotoCAP test protocols. The table below shows the test results for each strike on each impact protector in kilonewtons (kN) and their area of coverage as a proportion (%) of the Zone.

Impact protector type	Elbow	Shoulder
Average force (kN)	21.1 A	25.7 M
Maximum force (kN)	30.2 P	34.3 P
Coverage of zone 1 area	130%	80%
Coverage of zone after displacement	80%	70%

Individual test results

Impact force (kN)	Elbow			Shoulder		
Strike location	Α	В	С	Α	В	С
Impact Protector 1	17.5	18.6	30.2	17.7	23.9	34.3
Impact Protector 2	18.4	19.0	26.0	19.1	30.2	29.3
Impact Protector 3	17.3	18.6	24.6	18.8	24.2	33.5

The diagram below is a visual indication of the likely performance of each impact protector calculated from the data in the table above. The colour coding is based on the worst performing score for average or maximium force for each impact zone.



^{*} Poor may also indicate that no impact protector, or impact protector pocket is present in the garment Areas shaded black are not considered in the impact protection ratings.



Thermal comfort

The garment was tested for thermal comfort following the MotoCAP test protocols. The table below shows the moisture vapour resistance and the thermal resistance values obtained.

	1	2	Average
Moisture Vapour Resistance - Ret	239.0	207.3	223.2
(kPam²/W)			
	1	2	Average
Thermal Resistance - R _{ct}	0.350	0.308	0.329
(Km²/W)			

Water spray and rain resistance

This garment is advertised as water-resistant, and so has been tested for water spray and rain resistance according to the MotoCAP test protocols. The table below shows the water absorbed (ml) and the wetting proportion (%) of the garment and undergarments due to water absorption.

	Water absorbe	ed by garment	Water absorbed by underwear		
	Volume (ml) Percentage (%)		Volume (ml)	Percentage (%)	
Garment 1	529	42%	47	17%	
Garment 2	578	48%	61	22%	
Average	369	45%	36	20%	

Location of wetting:

Visible wetting to the cotton underwear worn under the motorcycle water-resistant garment was present over the chest on both garments tested.