This MotoCAP safety rating applies to:

Brand:	Draggin Jeans
Model:	Cargo
Type:	Pants - Denim
Date purchased:	7 August 2019
Sizes tested:	38 and 40
Gender:	M
Style:	All Purpose
Test code:	P19D04

Test Results Summary:

	Rating	Score
MotoCAP Protection Rating	★	19.5
Abrasion	3/10	2.30
Burst	8/10	801
Impact	0/10	0.0
MotoCAP Comfort Rating	★★★	0.500
Moisture Vapour Resistance		17.9
Thermal Resistance		0.149
Water resistance	N/A	N/A

This garment is fitted with pockets at the knees for aftermarket impact protectors. Pockets are not provided at the hips for aftermarket impact protectors. There are no vents to allow airflow movement through the garment.

Jacket and Pants - Crash Impact Risk Zones

This diagram is a pictorial representation of the crash impact risk Zones.



Zone 1	Zone 2	Zone 3	Zone 4
High risk of abrasion High risk of impact	High risk of abrasion	Medium risk of abrasion	Low risk of abrasion

Abrasion Resistance

The garment was tested for abrasion resistance in accordance with MotoCAP test protocols. The table below shows the test results for time to abrade through all layers of the materials. Calculated for each sample by Zone, type and area coverage of each material as a proportion of that Zone.

Details of materials used in garment:

Material A:	Cotton fabric shell, aramid fabric layer and mesh inner liner
Material B:	Cotton fabric shell

Zone	Coverage (%)	Abrasion time for each test (seconds) 1	2	3	4	5	6	Average (seconds)	
Zone 1 and 2 areas (High abrasion risk)									
Material A	100%	4.10	3.26	2.95	3.02	4.36	4.54	3.71	A
Zone 3 area (Medium abrasion risk)									
Material B	100%	0.26	0.15	0.16	0.20	0.19	0.16	0.19	P
Zone 4 area (Low abrasion risk)									
Material B	100%	0.26	0.15	0.16	0.20	0.19	0.16	0.19	P

Abrasion times are capped at a maximum of 10.00s.

The diagram below is a visual indication of the likely abrasion performance of the materials in each zone calculated from the data in the table above. The colour coding is based on the worst performing material in each zone.

Determining Criteria		Good	Acceptable	Marginal	Poor
High abrasion risk	Zone 1/2:	> 5.6	3.0 - 5.6	1.3 - 2.9	< 1.3
Medium abrasion risk	Zone 3:	> 2.5	1.8 - 2.5	0.8 - 1.7	< 0.8
Low abrasion risk	Zone 4:	>1.5	1.0 - 1.5	0.4 - 0.9	< 0.4

Burst Strength

The garment's burst strength was tested in accordance with MotoCAP test protocols. The table below shows the burst pressure in kilopascals (kPA) for each sample tested by Zone and the average result for each zone.

Burst pressure (kPA)

Area	1	2	3	4	5	Average	
Zones 1 & 2	748	1068	901	1035	677	886	A
Zone EZ	636	795	757	1039	748	795	M
Zones 3 & 4	880	632	650	412	648	645	M

The diagram below illustrates the burst strength results in terms of the likely performance of the garment in an impact and is a pictorial representation of the data from the table above.

Determining Criteria		Good	Acceptable	Marginal	Poor
Burst strength	(kPa)	> 1000	800 - 1000	500 - 799	< 500

Impact Protection

This garment was not tested for impact protection as impact protectors were not provided with the garment. The table below shows the test results for each strike on each impact protector in kilonewtons (kN) and their area of coverage as a proportion (%) of the Zone.

Impact protector type	Knee	Hip
Average force (kN)	P	P
Maximum force (kN)	P	P
Coverage of zone 1 area	0%	0%
Coverage of zone after displacement	0%	0%

Individual test results

Impact force (kN)	Knee	No impact protector present		Hip	No impact protector present	
Strike location	**A**	**B**	**C**	**A**	**B**	**C**
Impact Protector 1						
Impact Protector 2						
Impact Protector 3						

The diagram below is a visual indication of the likely performance of each impact protector calculated from the data in the table above. The colour coding is based on the worst performing score for average or maximium force for each impact zone.

Determining Criteria		Good	Acceptable	Marginal	Poor*
Impact force	(kN)	< 15	15 - 24	25 - 30	> 30

* Poor may also indicate that no impact protector, or impact protector pocket is present in the garment

Areas shaded black are not considered in the impact protection ratings.

Thermal comfort

The garment was tested for thermal comfort following the MotoCAP test protocols. The table below shows the moisture vapour resistance and the thermal resistance values obtained.

	1	2	**Average**
Moisture Vapour Resistance - R_{et} ($kPam^2/W$)	18.0	17.7	17.9

	1	2	**Average**
Thermal Resistance - R_{ct} (Km^2/W)	0.146	0.151	0.149

Water spray and rain resistance

This garment has not been advertised as water resistant so has not been tested for water spray and rain resistance.