


This MotoCAP safety rating applies to:


Brand	RST
Model	Sabre CE
Type	Pants - Leather
Date purchased	15 February 2022
Sizes tested	46 and 58
Test garment gender	Male
Style	Sports
RRP	\$399.99

Test Results Summary	Rating	Score
MotoCAP Protection Rating	★★★★★	67.2
Abrasion	10/10	7.28
Burst	10/10	1535
Impact	7/10	51.5
MotoCAP Breathability Rating	★★	0.345
Moisture Vapour Resistance	-	35.2
Thermal Resistance	-	0.202
Water resistance	N/A	N/A

This garment is fitted with impact protectors for the knees and hips. Replacing the knee armour with higher performing impact protectors would improve the protection levels of this garment. Perforated leather is located in the front of upper legs to allow airflow movement through the garment.

Jacket and Pants - Crash Impact Risk Zones

This diagram is a pictorial representation of the crash impact risk Zones.



Zone 1

 High risk of abrasion
 High risk of impact

Zone 2

 High risk of abrasion

Zone 3

 Medium risk of abrasion

Zone 4

 Low risk of abrasion

Removable liners

Thermal liner	<input type="checkbox"/>
Water-resistant liner	<input type="checkbox"/>

Removable impact protection

	Pockets	Armour
Knee	<input checked="" type="checkbox"/>	<input checked="" type="checkbox"/>
Hip	<input checked="" type="checkbox"/>	<input checked="" type="checkbox"/>

Abrasion Resistance

These pants were tested for abrasion resistance in accordance with MotoCAP test protocols. The diagram below is a visual indication of the likely abrasion performance of the materials in each zone calculated from the data in the table below. The colour coding is based on the worst performing material in each zone.



Abrasion Resistance Performance

Abrasion rating	10/10
Abrasion score	7.28

Determining Criteria	Area	Good	Acceptable	Marginal	Poor
High abrasion risk	Zones 1 & 2	> 5.6	3.0 - 5.6	1.3 - 2.9	< 1.3
Medium abrasion risk	Zone 3	> 2.5	1.8 - 2.5	0.8 - 1.7	< 0.8
Low abrasion risk	Zone 4	>1.5	1.0 - 1.5	0.4 - 0.9	< 0.4

Individual Abrasion Resistance Results: - The table below shows the test results for time to abrade through all layers of the materials. Calculated for each sample by Zone, type and area coverage of each material as a proportion of that Zone. Abrasion times are capped at a maximum of 10.00s.

Abrasion time for each test (seconds)

Zones 1 & 2	Coverage (%)	Sample 1	Sample 2	Sample 3	Sample 4	Sample 5	Sample 6	Average	
Material A	30%	10.00	10.00	10.00	10.00	10.00	10.00	10.00	G
Material B	70%	10.00	10.00	10.00	10.00	10.00	10.00	10.00	G
Zone 3	Coverage (%)	Sample 1	Sample 2	Sample 3	Sample 4	Sample 5	Sample 6	Average	
Material C	80%	3.44	4.26	5.15	3.30	4.94	2.58	3.94	G
Material D	20%	2.84	2.69	2.83				2.78	G
Zone 4	Coverage (%)	Sample 1	Sample 2	Sample 3	Sample 4	Sample 5	Sample 6	Average	
Material C	50%	3.44	4.26	5.15	3.30	4.94	2.58	3.94	G
Material E	50%	0.83	0.78	0.66	0.76	0.77	0.78	0.76	M

Details of materials used in jacket

Material A	Velcro patch over leather shell, leather layer, foam layer and fabric inner layer
Material B	Leather patch over leather shell with mesh inner layer
Material C	Leather shell with mesh inner layer
Material D	Perforated leather shell with mesh inner layer
Material E	Stretch fabric shell with mesh inner layer

Burst Strength

These pants were tested for burst strength in accordance with MotoCAP test protocols. The diagram below illustrates the burst strength results in terms of the likely performance of the garment in an impact and is a pictorial representation of the data from the table below.



Burst Strength Performance

Burst rating	10/10
Burst score	1535

Determining Criteria	Unit	Good	Acceptable	Marginal	Poor
Burst strength	(kPa)	> 1000	800 - 1000	500 - 799	< 500

Individual Burst Strength Results: - The table below shows the burst pressure in kilopascals (kPA) for each sample tested by Zone and the average result for each zone.

Burst pressure for each seam (kPA)

Area	Sample 1	Sample 2	Sample 3	Sample 4	Sample 5	Sample 6	Average	
Zones 1 & 2	2012	1824	2001	772	1214	1490	1552	G
Zones 3 & 4	1565	1431	1168	1020	1605	2006	1466	G

Impact Protection

These pants were tested for impact protection and coverage in accordance with MotoCAP test protocols. The diagram below is a visual indication of the likely performance of each impact protector calculated from the data in the table below. The colour coding is based on the worst performing score for average or maximum force for each impact zone. Areas shaded black are not considered for impact protection ratings.



Impact Protection Performance

Impact rating	7/10
Impact score	51.5

Determining Criteria	Unit	Good	Acceptable	Marginal	Poor*
Impact force	(kN)	< 15	15 - 24	25 - 30	> 30

* Poor may also indicate that no impact protector, or impact protector pocket is present in the garment

Impact Protector Results: - The table below shows the average and maximum force transmitted through each impact protector type in kilonewtons (kN) and their area of coverage as a proportion (%) of the Zone.

Impact protector type	Knee		Hip	
Average force (kN)	23.0	A	10.3	G
Maximum force (kN)	25.4	M	12.3	G
Coverage of Zone 1 area	110%		130%	
Coverage of Zone after displacement	100%		100%	

Individual Impact Protector Results: - The table below shows the test results for each strike on individual impact protectors in kilonewtons (kN) and the position of the strike. Individual strike results are capped at a maximum of 50kN.

Force transfer for each impact strike (kN)

Impact protector type	Knee			Hip		
	Centre	Mid	Edge	Centre	Mid	Edge
Impact Protector 1	21.4	21.8	25.4	9.2	10.0	11.4
Impact Protector 2	22.2	22.2	23.3	9.1	10.2	12.3
Impact Protector 3	23.9	23.0	24.0	9.1	9.7	11.4

Breathability

These pants were tested for breathability following the MotoCAP test protocols. The table below shows the moisture vapour resistance and the thermal resistance values obtained.

Without removable liners		With water-resistant liner	
Breathability rating	★★	Breathability rating	N/A
Breathability score	0.345	Breathability score	N/A

Moisture Vapour Resistance - R_{et} (kPa.m ² /W)	1	2	Average
Without removable liners	35.1	35.3	35.2
With water-resistant liner	N/A	N/A	N/A
Thermal Resistance - R_{ct} (K.m ² /W)	1	2	Average
Without removable liners	0.205	0.199	0.202
With water-resistant liner	N/A	N/A	N/A

Water spray and rain resistance

This pants have not been advertised as water-resistant so has not been tested for water spray and rain resistance.

Assessment Details.

Brand	RST
Model	Sabre CE
Type	Pants - Leather
Date purchased	15 February 2022
Tested by	AMCAF, Deakin University
Report approved by	MotoCAP Chief Scientist
Garment test reference	P20L07
Rating first published	July 2022
Rating updated	25 July 2022